


Deformed Bar



Imperial Diameter "D"	Metric Diameter "D"	Minimum Length "L"	Burn Of Flat	Est. Burn* Off
3/8	10mm	8.125	.125	N/A
1/2	13mm	8.125	.125	N/A
5/8	16mm	12.187	.125	N/A
3/4	20mm	12.187	.187	N/A

* Approximate values
Other sizes available
Contact us if you have a special requirement

Material:

Low Carbon Steel	
Material:	ASTM A496 C1010-C1020 C-0.23% max; P-0.04% max MN-0.90% max; S-0.05% max
Mechanical Properties:	Minimum Tensile80,000 psi (552 Mpa) Minimum Yield70,000 psi (485 MPa)